



Brillante pelliccia morbida di lamé trasparente da utilizzare da solo o per intervento. Possono essere riprodotti tutti i colori a campione cliente. La sua speciale struttura evidenzia una brillante rifrazione.

Brilliant soft fur in transparent lamé for use by itself or for inserts. These yarns can be reproduced in all the colors to the customers' samples. The special structure reveals a pearly refraction.

COTTE OTTIMALI - OPTIMAL DYE LOTS

NEON NM 10 100% NYLON

KG: 9* - 18* - 36* - 54* - 108

TITOLO NOMINALE - NOMINAL COUNT

*CON SUPPLEMENTO - *WITH SURCHARGE

INDICAZIONI PER L'UTILIZZO:

MACCHINA RETTILINEA FINEZZA 7 - 10 AD UN CAPO

LA LAVORAZIONE SEAMLESS HA MAGGIORI CRITICITA' DA DOVER VALUTARE DOPO LE VOSTRE PROVE CON IL NOSTRO UFFICIO TECNICO. LAVORARE ESCLUSIVAMENTE A PIU' GUIDAFILI ALTERNATI PER COMPENSARE LA RIFRAZIONE DI COLORE, LA MAGGIORE TOLLERANZA DEL TITOLO +/- 10% E L'ALTEZZA DEL TAGLIO, CARATTERISTICA STRUTTURALE DEI FILI CON EFFETTO CINIGLIA O TAGLIATI.

NON RIPARAFFINARE: NELL'EVENTUALITA' DI RIROCCARE, ROCCARE SEMPRE 2 VOLTE PER NON INVERTIRE IL SENSO DEL FILATO, USANDO GUIDAFILI AD ANELLO CHIUSO. EVENTUALE RIPARAFFINATURA USARE TENSIONE ADEGUATA PER OTTENERE ROCCHIE MORBIDE. VALUTARE ATTENTAMENTE L'IMPATTO DEI NODI SUL CAPO IN QUANTO LA COSTRUZIONE ARTIGIANALE DEL FILATO NE DETERMINA LA PRESENZA.

CARATTERISTICHE TECNICHE:

TARIFFA DOGANALE: 56060099

PESO A MQ 238 GR. RELATIVO AL TELO DI CAMPIONARIO, PUNTO RASATO TRATTATO FIN. 7. ICI PILLING BOX TEST: UNI EN ISO 12945-1 (14400 GIRI) VALORE PILLING: 4 / 5 RELATIVO AL TELO DI CAMPIONARIO, PUNTO RASATO TRATTATO.

TIPO DI NODI: MANUALI. NUMERO MEDIO DI NODI PER ROCCA: 3 / 4 PER TIPOLOGIE SPECIALI, CINIGLIE, TAGLIATI E NASTRI FANTASIA UNO SCARTO DEL 8 - 10% È DA RITENERSI NELLA NORMA.

ISTRUZIONI DI TRATTAMENTO INDUSTRIALE RIFERITE AL NOSTRO CAMPIONARIO:

VAPORIZZARE ADEGUATAMENTE. TRATTAMENTO: 5 MINUTI, RAPPORTO BAGNO 1/20 (MATERIALE/ACQUA) - TEMPERATURA: 22° C. AMMORBIDENTE: CATIONICO, CIRCA 3% PESO MATERIALE - ASCIUGATURA: 50° C. I VARI PUNTI MAGLIA CONDIZIONANO IL RIENTRO AL LAVAGGIO. SI RACCOMANDA UN CONTROLLO PRELIMINARE ALLA PRODUZIONE INDUSTRIALE, IN MODO DA OTTIMIZZARE LE RESE PER LE QUALI NON SIAMO RESPONSABILI. E' RACCOMANDATO IL TRATTAMENTO IN ACQUA IN MODO DA GARANTIRE LA STABILITA' DIMENSIONALE DEI CAPI.

INDICATIONS FOR USE:

FLAT KNITTING MACHINE GAUGE 7 - 10 FOR 1 PLY

THE SEAMLESS KNITTING IS MORE CRITICAL, PLEASE EVALUATE YOUR TESTS WITH CARE AND THEN WITH OUR TECHNICAL DEPARTMENT. KNIT EXCLUSIVELY USING MORE THREATGUIDES, IN ALTERNATION WITH EACH OTHER, IN ORDER TO COMPENSATE THE COLOR REFRACTION, THE HIGHER TOLERANCE OF THE COUNT +/- 10% AND THE HIGHT OF THE CUT OF THE HAIR STRUCTURAL CHARACTERISTIC OF YARNS WITH CHENILLE EFFECT OR CUT FIBRES.

DO NOT RE-WIND. IN CASE OF RE-WINDING ALWAYS RE-WIND TWICE IN ORDER NOT TO REVERSE THE HAIR DIRECTION, USING RING YARN GUIDE. IN CASE OF RE- WAXING, APPLY THE CORRECT REGISTRATION IN ORDER TO OBTAIN SOFT CONES. CAREFULLY CONSIDER THE IMPACT OF THE KNOTS ON THE GARMENT BECAUSE THE ARTISAN CONSTRUCTION OF THE YARN DETERMINES THEIR PRESENCE.

TECHNICAL NOTES:

CUSTOMS CODE: 56060099

SQ. METER WEIGHT: 238 GR. REFERRING TO SAMPLE JERSEY STITCH WASHED GG. 7. ICI PILLING BOX TEST: UNI EN ISO 12945-1 (14400 TURNS) 4 / 5 PILLING VALUE, REFERRING TO SAMPLE JERSEY STITCH WASHED.

KIND OF KNOTS: MANUAL. AVERAGE NUMBER OF KNOTS PER CONE: 3 / 4 FOR SPECIAL YARNS, CHENILLE, CUT AND RIBBON YARNS A WASTE OF 8 - 10% CAN BE CONSIDERED NORMAL.

INDUSTRIAL FINISHING INSTRUCTIONS REFERRED TO OUR COLLECTION:

STEAM ADEQUATELY. TREATMENT: 5 MINUTES, BATH RATIO 1/20 (MATERIAL/WATER) - TEMPERATURE: 22° C. SOFTENERS: CATIONIC, ABOUT 3% OF MATERIAL WEIGHT - DRY: 50° C. SHRINKING AFTER WASHING DEPENDS ON THE KIND OF STITCH USED. WE RECOMMEND TO CHECK IT BEFORE ENTERING BULK PRODUCTION, SO AS TO OPTIMIZE THE PERFORMANCES FOR WHICH WE DO NOT REMAIN RESPONSIBLE. WE RECOMMEND A TREATMENT IN WATER SO AS TO GUARANTEE THE DIMENSIONAL STABILITY OF GARMENTS.

SOLIDITA' : VALORI MEDI INDICATIVI - FASTNESS: INDICATIVE AVERAGE VALUES

LAVAGGIO IN ACQUA A 30°C. WATER WASHING AT 30°C. (UNI EN ISO 105 C06)	3	LAVAGGIO A SECCO DRY CLEANING (UNI EN ISO 105 X05)	4
LUCE LIGHT (UNI EN ISO 105 B02)	3 - 4	TINTO MATASSA HANK DYED	

PER COLORI CHIARI E BIANCO, LA SOLIDITA' ALLA LUCE E' INFERIORE DI CIRCA 1 PUNTO DAI VALORI INDICATIVI DELLA SCHEDA CHE SI RIFERISCONO AI COLORI DELLA CARTELLA. LE SOLIDITA' DEI COLORI A CAMPIONE VA DEFINITA CON I NOSTRI UFFICI COMMERCIALI.

SUDORE ALCALINO ALKALINE PERSPIRATION (UNI EN ISO 105 E04)	3	SUDORE ACIDO ACID PERSPIRATION (UNI EN ISO 105 E04)	3
SFREGAMENTO A SECCO DRY RUBBING (UNI EN ISO 105 X12)	3	SFREGAMENTO A UMIDO WET RUBBING (UNI EN ISO 105 X12)	3

FOR LIGHT AND WHITE COLORS THE FASTNESS TO LIGHT IS LOWER OF APPROX. 1 POINT FROM THE INDICATIVE VALUES OF THE TECHNICAL SHEET WHICH REFER TO COLOR CARD COLORS. THE FASTNESS OF SPECIAL COLORS MUST BE CONFIRMED WITH OUR SALES OFFICES.

ISTRUZIONI DI MANUTENZIONE:

CAPI IN TINTA UNITA: LAVARE DELICATAMENTE A SECCO OPPURE IN ACQUA A 30°C. CON SAPONE NEUTRO. CAPI RIGATI O COLORI CONTRASTANTI: E' RACCOMANDATO IL LAVAGGIO A SECCO, ADEGUANDO I SIMBOLI DI MANUTENZIONE. RIVOLGERSI ALL'UFFICIO COMMERCIALE PER VALUTARE LA POSSIBILITA' DI TRATTAMENTI E COSTI, PER RAGGIUNGERE SOLIDITA' MAGGIORI. ASCIUGARE IN PIANO SUBITO DOPO IL LAVAGGIO. NON ESPORRE CAPI UMIDI A LUCE DIRETTA.

CARE INSTRUCTIONS:

ONE COLOUR GARMENTS: DRY CLEAN DELICATELY OR WASH IN 30°C. WATER WITH NEUTRAL SOAP. STRIPED OR MORE COLOUR GARMENTS: WE RECOMMEND DRY CLEAN ADAPTING THE CARE SYMBOLS. PLEASE CONTACT THE SALES OFFICE TO EVALUATE THE POSSIBILITY OF TREATMENTS AND COSTS TO ACHIEVE HIGHER FASTNESS. DRY FLAT, IMMEDIATELY AFTER WASHING. DO NOT EXPOSE WET GARMENTS TO DIRECT LIGHT.

SIMBOLI DI MANUTENZIONE INTERNAZIONALI - UNI EN ISO 3758 : 2012 - INTERNATIONAL CARE SYMBOLS

CAPI IN TINTA UNITA								ONE COLOUR GARMENTS
CAPI RIGATI O COLORI CONTRASTANTI								STRIPED OR MORE COLOUR GARMENTS

filati BE.MIVA.